

Data	Unit	Value	Test Method
Colour	-	Carbon	-
Thickness	Micron	38	F2251-13
Impact Strength Peak Load	Kg	15	D3763-15
Clarity Total Transmittance	%	0-4 0-4	D1746-15 D1003-13
Coefficient of Friction	(Film/stainless, kinetic)	0.132	D-1894-95
Burst Strength	Kg/cm <sup>2</sup>	1.26	D3763-15
<b>LD/TD</b>			
Tensile Strength	Kg/cm <sup>2</sup>	1055/1265	D-882-95

LD = Longitudinal Direction/ TD = Transverse Direction

All statements or recommendations are based on data and knowledge considered to be true and accurate at the time of printing but should be verified by the user. Since the conditions of use are beyond our control we do not warrant: the completeness of any statement or recommendation, or as regards the goods or services supplied by us, the suitability for any intended purpose or the results to be obtained. Please read all statements or recommendations in conjunction with our conditions of sale including those limiting warranties and remedies which apply to all goods and services supplied by us. No statement or recommendation is intended for any use, which would violate or infringe statutory obligations or rights belonging to third parties.